

RUGISTOP

RUST CONVERTER

code 5900100

DESCRIPTION

RUGISTOP is an emulsion-based product which transforms rust into metal-organic compounds which adhere perfectly to the surface.

RUGISTOP enables rust to be stopped on surfaces which are not easy to clean, doing away with the need for tiring sanding and buffing.

The product is suitable for treating ferrous surfaces such as railings, radiators, car bodies, etc.. The product is easy to apply and does not ruin painted parts.

INSTRUCTIONS FOR USE

The product can be applied on ferrous surfaces in general.

TECHNICAL SPECIFICATIONS

- Specific gravity per UNI EN ISO 2811-1: 1.03 ± 0.02 kg/l
- Outflow rate UNI 8356: 12-13" Ford cup n 4 at 25 C
- Appearance: milky liquid
- Drying (at 25 C and 65% R.H.): touch dry after 2 hours; coatability after 24 hours and no more than 4 weeks after application.

PREPARING THE SURFACE

Ferrous metal:

- Remove any compact and adherent calamine.
- Remove any grease from the surfaces using nitro thinner.
- Apply the RUGISTOP rust converter.

APPLICATION INSTRUCTIONS

Air and surface conditions:

Air temperature: Min. +5 C / Max. +35 C.

Relative humidity of the air: <80%.

Temperature of the surface: Min. +5 C / Max. +35 C.

Dry surface.

- Stir the product before use.
 - The product can be applied with a brush, or applied by means of roller coating or spraying.
 - Thinning: ready to be used.
 - N coats: a single coat should be applied.
 - Tools should be cleaned immediately after use using water.
 - Indicative spreading rate: 8-10 sq m/l on smooth surfaces.
- It is advisable to perform a preliminary test on the specific surface in order to determine the actual consumption.

TINTING

STORAGE

Maximum temperature for storage stability: +30 °C

Minimum temperature for storage stability: +5 °C

The product should be preferably used within 2 years from date of manufacture when stored in original unopened containers and in appropriate temperature conditions.

SAFETY RULES

Does not fall under EU directive 2004/42 (legislative decree 161/2006)

Use the product according to current health and safety regulations; after use, do not discard the containers in the environment; allow the residue to dry thoroughly, then treat as special waste. Do not dispose of residues in the sewers, waterways or ground. For more information consult the safety data sheet.

SPECIFICATION ITEM

Application, on ferrous surfaces affected by rust, of RUGISTOP Rust converter cod. 5900100, for converting rust on areas which are hard to clean.

Supply and application €..... sq m.

SAN MARCO GROUP guarantees that the information herein is provided to the best of its technical and scientific knowledge and based on its experience; nonetheless, the company may not be held liable for the results obtained using these products, as application conditions are beyond its control. It is recommended to always make sure that the product is suited to each specific instance. The present sheet voids and replaces any previously existing sheets. For further technical information call the technical service +39 041 4569322.